DelS lar

D6E **Mono-crystalline Photovoltaic Cell**

A full range of cell processing, including

- Mono-crystalline Silicon-based cell
- 6 inch cell size with 2 busbars
- Wafer thickness of 180 to 200 μm

High efficiency and thin wafer handling capabilities

- Dynamic optimized setting system
- Soft-touch wafer handling system

Robust-in-house automation systems

- Improved quality, efficiency and yield increase
- Highly automated wafer transport system



About DelSolar

Established as a subsidiary of Delta Electronics, Inc., the world's number one switching power supplies provider, DelSolar is dedicated to the research, development, and production of high-quality solar cells, modules, and photovoltaic (PV) systems. DelSolar strives to become the world's leading solar supplier through continuous innovation, outstanding production processes, high yield rates, and world-class product efficiency. Under its parent company's leadership, DelSolar is committed to providing clean and effective solar energy for a sustainable world.

More Information, please visit us at: www.delsolarpv.com

Contact Us

Global Contact (Headquarters) Tel: +886-37-539999 Email: sales@delsolarpv.com

US Contact Tel: +1-888-880-8868

Europe Contact Tel: +31 (0)20 6550953 Email: solar.sales@delta-corp.com Email: sales.europe@delsolarpv.com

DelSòlar

Mechanical Specification

Item	Spec
Product	Mono-crystalline silicon solar cell
Dimension	156 mm x 156 mm ± 0.5 mm
Thickness	200 μm ± 30 μm
Front	2.0 ± 0.1 mm busbar (silver) Silicon nitride antireflection coating
Back	2.5 mm dashed line soldering pads (silver) Back surface field (aluminum)

Electrical Properties

Efficiency (%)	P _{mpp} (W)		l _{sc} (A)	l _{min} (A)
20.0	4.78	0.646	9.30	9.05
19.8	4.73	0.644	9.24	8.98
19.6	4.68	0.642	9.18	8.91
19.4	4.64	0.640	9.12	8.84
19.2	4.59	0.638	9.06	8.77
19.0	4.54	0.637	9.00	8.70
18.8	4.49	0.635	8.94	8.63
18.6	4.44	0.633	8.88	8.56
18.4	4.40	0.631	8.82	8.49
18.2	4.35	0.630	8.72	8.40
18.0	4.30	0.629	8.62	8.32

* Testing conditions: 1000 W/m², AM 1.5, 25 °C, Tolerance: Efficiency ± 0.2% abs., $P_{_{mpp}}$ ±1.5% rel. * $I_{_{mm}}$: at 0.5 V

Light Intensity Dependence

Intensity W/m ²	V _{mpp} *	* mpp
1000	1.00	1.00
800	0.99	0.80
600	0.99	0.60
400	0.97	0.40
200	0.94	0.20

* Ratio of $V_{\rm mpp}/I_{\rm mpp}$ at reduced intensity to $V_{\rm mpp}/I_{\rm mpp}$ at 1000 W/m²

Soldering Ability

Peel Strength: > 1.0 N/mm (Pull soldered ribbon from busbar in 5 mm/s of 180°)

Dimension





Spectral Response



I-V Curves



Temperature Coefficients

Item	Spec
Current	0.05 %/°K
Voltage	-0.34 %/°K
Power	-0.43 %/°K